



## **Technical Data Sheet**

# **NC Clear Matt**

Product code: E/138X

Color: Transparent Finish: Matt

#### **Composition and Application Field**

Clear matt nitroalkyd topcoat finish, indicated for furniture (modern and old style), frames and wooden manfactures of different nature. Endowed with a very good covering, plasticity, softness and excellent hardness.

Available in the following versions

E/1380 6±1% Gloss E/1381 12±3% Gloss E/1382 30±5% Gloss E/1383 50±5% Gloss E/1384 70±5% Gloss

# Product Preperation Additive

Not necessary in normal condition of use, but they are several in order to increase drying or better leveling...

### **Dilution**

Spraying: Dilute with NC thinner at 100%

Curtain Coater: We advise to dilute with NC thinner E/600 upto 80-100%

In case of hot and humidity climate to avoid pin-hole and blooming, add 3% of NC retardant thinner E/631.

#### **Technical Characteristics**

Physical Properties
Specific gravity

specific gravity	0.70	(± 0,023) Ng/1
* Viscosity. Brokfield	10000	(± 1000) Cps
DV11+, Spindle 4,		
RPM6 @ 25°C		
Weight solids	28%	(± 2) Kg/Kg
Flash Point	21	grades
		centiarade

0.96

(+ 0.025) Ka/l

(Abel Pensky closed cup)

Application Rate ...... 120gr/m² (per coat)

Drying @25°C

\* Dust free 10 mn
Touch drying 30 mn
Deep drying 4 hrs
Packing 12 hrs

**N.B:** Before packing control the working condition and do a preliminary test.

#### **Dry Film Characteristics**

Mechanical Characteritics

*	Gloss 60	)°	From 5 to 70 (ASTM $\Box$	)523/67)
	Adheren	ceVe	ery good (on wooden & sanc	ded substrates)
	Plasticity		Very good	
	Softness.		Very good	
	Surface HardnessVery good (according with type product)			

#### **Surface Preperation**

This product can be applied on well sanded bascecots nitocellulose or polyurethane based. As sanding paper use 220 grain type followed by parer 400 grain type. If have been used some ageing products as "patinas", be sure of drying before applying the NC topfinish.

#### **Application Method**

By spray: Use a spray gun with nozzle 1,8-2 mm. at 3-4 atm/bar. It is possible to use even air mix spray gun pump assisted.

By curtain coater: The most important is to keep steady the starting viscosity.

Respect time of interval coat and drying.

#### **Subsequent Treatments**

After drying the top finish does not need subsequent treatment. In case of maitenance in the time (expecially on old style furniture) it can be applied a wax product by rag.

#### **Packing**

Available in Usq, Usg, 5Usg and 10(5Usg)

### Storage

If the drum is hermetically closed and well stored at 25°C, the product has maximum 18 months of shelf-life.