



## **Technical Data Sheet**

# Acid Curing Pigmented Glossy

Product code: E/2185-Color

Color: Varieties of Color Finish: Glossy

#### **Composition and Application Field**

Pigmented Acid Curing glossy, a two - component, endowed with high solid contents and It is indicated to varnish furniture, doors, windows sush frames and casings where high durability and scratch resistance are required. It also has a good plasticity, good hiding power and high gloss.

**NB:** This product could be used as sealer and topcoat at the same time, because it represents a good sanding properties.

#### **Product Preperation**

Catalyst by weight by volume with hardener

10% 10% E/1000

Pot Life 6hrs. at 25°C

#### **Dillution**

Spraying: Dilute with NC thinner E/600 at 25%. Curtain Coater: Dilute with NC thinner E/600 at 20%.

#### **Technical Characteristics**

Physical Properties

| /                     | -                    |           |               |
|-----------------------|----------------------|-----------|---------------|
| Specific gravity      | (according to color) | 1.01-1.28 | (± 0,025) Kg/ |
| * Visc. Ford          | (according to color) | 70        | (± 5) Sec.    |
| 4/ 25°C               |                      |           |               |
| Weight solids         | (according to color) | 52-62%    | (± 2) Kg/Kg   |
| Weight solids blended | (according to color) | 48-56%    | (± 2) Kg/Kg   |
| Flash Point           |                      | 21        | grades        |
|                       |                      |           | centigrade    |

(Abel Pensky closed cup)

#### Drying @25°C

| * Dust free   | 15 mn  |
|---------------|--------|
| Touch drying  | 25 mn  |
| Interval coat | 2 hrs  |
| Deep drying   | 24 hrs |
| Polish        | 48 hrs |

#### **Dry Film Characteristics**

**Mechanical Characteritics** 

| Gloss 60°   | From 5 to 70 (ASTM D523/67) |
|-------------|-----------------------------|
| Hardness    | Very Good                   |
| Antiscratch | Very Good                   |
| Plasticity  | Very Good                   |
| Sanding     | Very Good                   |
|             |                             |

#### **Surface Preparation**

Good sanding for the wood before application of this product. Use sanding paper 120-150. Control the compatibility of stains eventually used. Apply the acid curing self sealer 2-3 cross coat according to the coverage required, the sealer should be sanded with sanding paper 220, followed by sanding paper 400, after that apply the topcoat one to two cross coats.

#### **Application Method**

Spray gun: Use a spray gun with 1.8 mm nozzle at 3-4 atm/bar of pressure. It can be used for airless or air-mix equipments.

Curtain Coater: It is very important to keep controlled the viscosity during the application, adding thinner to compensate the solvents evaporation.

The glossy finish can be applied in one coat or in two coats with an interval of 2 hrs. without sanding. After 2-3 hrs. it is necessary to sand between coats to avoid any inconvenience.

### **Subsequent Treatments**

After drying this product does not need any particular subsequent treatment, except for the eventually brushing and polishing treatment using proper abrasives.

#### Note

Using this product with E/1000, it can be treated even handicraft outdoor exposed. In this case take care to cover with varnish all the exposed parts, to prevent any type of infiltration. Only like this it is possible to have a product with good outdoor resistance, to take away in the time the defoiling of the varnish. Its most important characteristics are reduced formaldehyde emission, excellent wettability and the correct degree of conductivity for good wrapping in electrostatic application.

#### **Packing**

Available in 1 Usq, 1 Usg, 5 Usg.

#### Storage

If the drum is hermetically closed and well stored at 25°C, the product have 6 months of shelf-life.

The hardeners have 6 months of shelf-life.