

STUCCO PUTTY COARSE

Product code: PW2506

Composition and Application Field

EVI Stucco Putty Coarse is based on an acrylic copolymer formulated with pigments with good alkali resistant pigments. It is primarily used for filling surface irregularities, construction flaws, hairline surface cracks & indentations. The surface is rendered smooth and leveled with enough anchorage so as to apply a smooth layer of subsequent coats.

Use

Substrates: Concrete, plaster, masonry, gypsum, and wood works.

Area of Use: Interiors only

Specification

Finish	: Coarse & Buttery
Colour	: White to off White
Specific gravity	: 1.65 ± 0.02
Solids (% by volume)	: 42 ± 2
Diluent	: Sweet Water
Flash point	: Not Applicable

Spread Rate:

While the spread rate is directly dependent on the surface profile, and also the undulations it has, as a thumb rule **EVI Stucco Putty Coarse** would cover 3 square meters per liter @ 150 microns and may be taken for cost calculations.

Drying Time (30° C) : Set to touch: 30 minutes- 1 hour.

: Ready for Recoat: app 6-8 hours

Recommended DFT : 1-2 coats. App 100 – 150 mic per coat

Surface Preparation

A good surface preparation and following the method statement / recommended system procedure of EVI is an ideal recommendation for the application of **EVI Stucco Putty Coarse**.

For Plaster, Masonry & Concrete :

Achieve a good and clean surface by removing all contaminants by cleaning & drying. A laitance free surface should be achieved by good sweep blast or a wire brush. Before applying the **EVI Stucco Putty Coarse** apply one coat of **EVI PVA Primer Sealer** and allow drying.

For Wood & Timber:

Achieve a good and clean surface by removing all contaminants by cleaning & drying treatment with EVI Wood Preservative Compound is advisable. Start off with good coat of **EVI Wood Primer** and allow to dry well and apply required coats of **EVI Stucco Putty Coarse**. Exclusions for successful application include perpetually wet surfaces and also large cavities on wooden surfaces.

Application Method

Adequate ventilation is an ideal situation as it helps in drying and the good application itself. Avoid high humid conditions i.e., >95% when condensation is likely to interfere and also when the surface temperature is at least 3°C above dew point. One can add 5 to 10% of sweet water for ease of application depending on the suitability of application. One should apply with a putty knife or a board bladed knife and spread it evenly on the surface to smoothen. After application light sanding may done to remove the imperfections.

Paint System

EVI Stucco Putty Coarse	
-	EVI PVA Primer Sealer 1 coat
-	EVI Stucco Putty Coarse 2 coats
-	EVI Gold Emulsion 2 coats

Recommended system to be applied as per surface preparation. Or as per EVI technical advice.

Storage & Shelf Life

Under dry and cool condition, storage stability can be sound up to 18 months in original sealed containers.

HANDLING

Disposal: As per the guidance and legislations of the local Authority e.g., by controlled landfill. In case of doubt, consult local authority. Do not empty into drains, sewers or other water courses.

Flash Point: Not applicable

Safety Precaution

Avoid contact with the skin and eyes. Wear suitable protective clothing such as overalls, goggles, dust mask and gloves. Use a barrier cream. Ensure that there is adequate ventilation in the area where the product is being applied. Do not breathe vapors or spray. MSDS is available on request for the safe handling of this product.

FIRST AID

Eyes: In the event of accidental splashes, flush eyes with warm water immediately and obtain medical advice.

Skin: Wash skin thoroughly with soap and water or approved Industrial cleaner. DO NOT USE solvent or thinners.

Inhalation: Remove to fresh air, loosen collar and keep patient rested.

Ingestion: In case of accidental ingestion DO NOT INDUCE VOMITING. Obtain immediate medical attention.